



NAS 410 COURSE OUTLINES FOR PENETRANT AND MAGNETIC PARTICLE TESTING

Magnetic Particle Level I/II course Outline to meet NAS-410 training requirements (32hrs)

Penetrant Level I/II course Outline to meet NAS-410 training requirements (32hrs)

Objective:

- To provide the training necessary to meet the NAS-410 Revision 2 requirements of 32 hours training for each method.
- The training will discuss the codes, standards and specifications used by the attendees. These may include ASTM standards, Boeing specifications, Honeywell specifications, etc.
- Prior to the course, information will be obtained from the attendees regarding applicable codes, these codes will be available during the training.
- The training will consist of both theory and practical hands-on and will focus on performing the process control requirements associated with each code, etc.
- Attendees will also prepare written practice techniques and will write inspection reports of inspections performed.
- Techniques and reports generated by students will be in accordance with the individual's specification requirements, and will then be assessed by the Instructor.

Magnetic Particle Testing Level I / II Course Outline (32 hrs) as per NAS-410

Principles of Magnets and Magnetic Fields

- a. Theory of magnetic fields
 - (1) Earth's magnetic field
 - (2) Magnetic fields around magnetized materials
- b. Theory of magnetism
 - (1) Magnetic poles
 - (2) Law of magnetism
 - (3) Materials influenced by magnetic fields
 - (a) Ferromagnetic
 - (b) Paramagnetic
 - (4) Magnetic characteristics of nonferrous materials

- c. Terminology associated with magnetic particle testing

Characteristics of Magnetic Fields

- a. Bar magnet
- b. Ring magnet

Effect of Discontinuities of Materials

- a. Surface cracks
- b. Scratches
- c. Subsurface defects

Magnetization by Means of Electric Current

- a. Circular field
 - (1) Field around a straight conductor
 - (2) Right-hand rule
 - (3) Field in parts through which current flows (a) Long, solid, cylindrical, regular parts

- (b) Irregularly-shaped parts
- (c) Tubular parts
- (d) Parts containing machined holes, slots, etc.
- (4) Methods of inducing current flow in parts
 - (a) Contact plates
 - (b) Prods
- (5) Discontinuities commonly discovered by circular fields
- b. Longitudinal field
 - (1) Field produced by current flow in a coil
 - (2) Field direction in a current-carrying coil
 - (3) Field strength in a current-carrying coil
 - (4) Discontinuities commonly discovered by longitudinal fields
 - (5) Advantages of longitudinal magnetization
 - (6) Disadvantages of longitudinal magnetization

Selecting the Proper Method of Magnetization

- a. Alloy, shape, and condition of part
- b. Type of magnetizing current
- c. Direction of magnetic field
- d. Sequence of operations
- e. Value of flux density

Inspection Materials

- a. Wet particles
- b. Dry particles

Principles of Demagnetization

- a. Residual magnetism
- b. Reasons for requiring demagnetization
- c. Longitudinal and circular residual fields
- d. Basic principles of demagnetization
- e. Retentivity and coercive force
- f. Methods of demagnetization

Magnetic Particle Testing Equipment

- a. Equipment-selection considerations
 - (1) Type of magnetizing current
 - (2) Location and nature of test

- (3) Test materials used
- (4) Purpose of test
- (5) Area inspected
- b. Manual inspection equipment
- c. Medium- and heavy-duty equipment
- d. Stationary equipment
- e. Mechanized inspection equipment
 - (1) Semiautomatic inspection equipment
 - (2) Single-purpose semiautomatic equipment
 - (3) Multipurpose semiautomatic equipment
 - (4) Fully automatic equipment

Types of Discontinuities Detected by Magnetic Particle Testing

- a. Inclusions
- b. Blowholes
- c. Porosity
- d. Flakes
- e. Cracks
- f. Pipes
- g. Laminations
- h. Laps
- i. Forging bursts
- j. Voids

Magnetic Particle Test Indications and Interpretations

- a. Indications of nonmetallic inclusions
- b. Indications of surface seams
- c. Indications of cracks
- d. Indications of laminations
- e. Indications of laps
- f. Indications of bursts and flakes
- g. Indications of porosity
- h. Nonrelevant indications

Selecting the Proper Method of Magnetization Principles

- a. Theory
 - (1) Flux Patterns
 - (2) Frequency and voltage factors
 - (3) Current calculations
 - (4) Surface flux strength
 - (5) Subsurface effects
- b. Magnets and magnetism
 - (1) Distance factor vs. strength of flux

- (2) Internal and external flux patterns
- (3) Phenomenon action at the discontinuity
- (4) Heat effects on magnetism
- (5) Material Hardness vs. magnetic retention

Flux Fields

- a. Direct current
 - (1) Depth of penetration factors
 - (2) Source of current
- b. Direct pulsating current
 - (1) Similarity to direct current
 - (2) Advantages
 - (3) Typical fields
- c. Alternating current
 - (1) Cyclic effects
 - (2) Surface strength characteristics
 - (3) Safety precautions
 - (4) Voltage and current factors
 - (5) Source of current

Effects of Discontinuities on Materials

- a. Design factors
 - (1) Mechanical properties
 - (2) Part use
- b. Relationship to load carrying ability

Magnetization by Means of Electric Current

- a. Circular techniques
 - (1) Current calculations
 - (2) Depth-factor considerations
 - (3) Precautions – safety and overheating
 - (4) Contact prods and yokes
 - (a) Requirements for prods and yokes
 - (b) Current carrying capabilities
 - (5) Discontinuities commonly detected
- b. Longitudinal technique
 - (1) Principles of induced flux fields
 - (2) Geometry of part to be inspected
 - (3) Shapes and sizes of coils
 - (4) Use of coils and cables
 - (a) strength of field
 - (b) Current directional flow vs. flux field
 - (5) Current calculations
 - (a) Formulas
 - (b) Types of current required
 - (c) Current demand

- (6) Discontinuities commonly detected

Selecting the Proper Method of Magnetization

- a. Alloy, shape, and condition of part
- b. Type of magnetizing current
- c. Direction of magnetic field
- d. Sequence of operations
- e. Value of flux density

Demagnetizing Procedures

- a. Need for demagnetization of parts
- b. Current, frequency, and field orientation
- c. Heat factors and precautions
- d. Need for collapsing flux fields

Equipment

- a. Portable type
 - (1) Reason for portable equipment
 - (2) Capabilities of portable equipment
 - (3) Similarity to stationary equipment
- b. Stationary type
 - (1) Capability of handling large and heavy parts
 - (2) Flexibility in use
 - (3) Need for stationary equipment
 - (4) Use of accessories and attachments
- c. Automatic Type
 - (1) Requirements for automation
 - (2) Sequential operations
 - (3) Control and operation factors
 - (4) Alarm and rejection mechanisms
- d. Liquids and powders
 - (1) Liquid requirements as a particle vehicle
 - (2) Safety precautions
 - (3) Temperature needs
 - (4) Powder and paste contents
 - (5) Mixing procedures
 - (6) Need for accurate proportions
- e. Black-light type
 - (1) Black-light and florescence
 - (2) Visible- and black-light comparisons
 - (3) Requirements in the testing cycle
 - (4) Techniques in use
- f. Light-sensitive instruments
 - (1) Need for instrumentation
 - (2) Light characteristics

- d. Tests for black-light intensity

Types of Discontinuities

- a. In castings
- b. In ingots
- c. In wrought sections and parts
- d. In welds

Evaluation Techniques

- a. Use of standards
 - (1) Need for standards and references
 - (2) Comparisons of known and unknown
 - (3) Specifications and certifications
 - (4) Comparison techniques
- b. Defect appraisal
 - (1) History of part
 - (2) Manufacturing process
 - (3) Possible causes of defect
 - (4) Use of part
 - (5) Acceptance and rejection criteria
 - (6) Use of tolerances

Quality Control of Equipment and Process

- a. Malfunctioning of equipment
- b. Proper magnetic particles and bath liquid
- c. Bath concentration
 - (1) Settling test
 - (2) Other bath-strength tests

Process control checks covered will include:

Magnetic Particle –

- Black light intensity
- Ambient white light
- Ketos ring (or AS-5282 for Boeing)
- Particle concentration and adjustment
- Particle contamination
- Calibration status of all equipment (make list)

During the Magnetic Particle course amperage determination will be featured heavily, including calculations and using a Gauss meter.

Inspection Procedures and Standards

- a. Inspection procedures
- b. Standards/Codes
ASTM E 1444, BSS 7040

Practical demonstrations and structured daily exercises

Summary / Final review

End of Course Test and review

Material Reference:

Written material used to support this training course consists of the course manual written and prepared by Mr. R. Harrison with photographs courtesy of Met-I-Chek and Magnaflux.

Other sources:

ASNT NonDestructive Handbook
SNT-TC-1A 1996 & 2001
NAS-410 2003
Standards/Codes: ASTM E 1444, BSS 7040 & BSS 7698

The Magnetic Particle technique sheets will include amperage calculations and gauss meter readings.

The Magnetic Particle techniques sheets will include sketches of component for each shot (head, central conductor and coil).

The Magnetic Particle techniques will include L/D calculations and details of multiple component inspection techniques (e.g. multiple nuts on a central conductor for coil shots and bolts in non-metallic channels).

**Penetrant L /II Testing Course Outline
(32 hrs)**

Introduction

- a. Brief history of nondestructive testing and liquid penetrant testing
- b. Purpose of liquid penetrant testing
- c. Basic principles of liquid penetrant testing
- d. Types of liquid penetrants commercially available

Liquid Penetrant Processing

- a. Preparation of parts
- b. Adequate lighting
- c. Application of penetrant to parts
- d. Removal of surface penetrant
- e. Developer application and drying
- f. Inspection and evaluation
- g. Post cleaning

Various Penetrant Testing Methods

- a. Characteristics of each method
- b. General applications of each method

Liquid Penetrant Testing Equipment

- a. Liquid penetrant testing units
- b. Lighting for liquid penetrant inspection
- c. Materials for liquid penetrant testing
- d. Precautions in liquid penetrant inspection

Review

- a. Basic Principles
- b. Process of various methods
- c. Equipment

Selection of Appropriate Penetrant Testing Method

- a. Advantages of various methods
- b. Disadvantages of various methods

Inspection and Evaluation of Indications

- a. General
 - (1) Discontinuities inherent in various materials
 - (2) Reasons for indications

- (3) Appearance of indications
- (4) Time for indications to appear
- (5) Persistence of indications
- b. Factors affecting indications
 - (1) Penetrant used
 - (2) Prior processing
 - (3) Technique used
- c. Indications from cracks
 - (1) Cracks occurring during solidification
 - (2) Cracks occurring during processing
 - (3) Cracks occurring during service
- d. Indications from porosity
- e. Indications from specific material forms
 - (1) Forgings
 - (2) Castings
 - (3) Plate
 - (4) Welds
 - (5) Extrusions
- f. Evaluation of indications
 - (1) True indications
 - (2) False indications
 - (3) Relevant indications
 - (4) Nonrelevant indications

Inspection Procedures and Standards

- c. Inspection procedures
- d. Standards/Codes
 - ASTM E 1417,AMS 2644,
 - BSS 7039,BAC 5423

Practical demonstrations and structured daily exercises

Summary / Final review

End of Course Test and review

Material Reference:

Written material used to support this training course consists of the course manual written and prepared by Mr. R. Harrison with photographs courtesy of Met-I-Chek and Magnaflux.

Other sources:

ASNT Nondestructive Handbook
SNT-TC-1A 1996 & 2001
NAS-410 2003

Standards/Codes: ASTM E 1417& AMS 2644
BSS 7039, BAC 5423 & BSS 7698

Process control checks covered will include:

Penetrant -

- Processing TAM panels through WW and PE process.
- Checking black light intensity
- Ambient white light checks
- Condition of Penetrant
- Construct Post Emulsified Hydrophilic concentration graph and use it to check in-use concentration.
- Document water pressure and temperature checks
- Drying oven temperature checks
- Calibration status on all equipment – make list
- Dry powder contamination and condition

During the Penetrant course, strict attention to the dwell times and emulsifier times should be made as per the specifications.